

Claims

What is claimed is:

1. A radiation curable composition comprising:
- 5 (i) at least one radiation-curable oligomer; and
- (ii) 0-20 wt%, relative to the total weight of the composition, of monofunctional reactive diluents;
- wherein said composition has
- a viscosity of less than 10,000 cps at 25 °C; and, after cure,
- a secant modulus of less than 5 MPa.
- 10 2. The composition of claim 1, comprising less than 10 wt% of said monofunctional reactive diluents.
3. The composition of claim 1, wherein said composition comprises less than 5
- 15 wt% of said monofunctional reactive diluents.
4. The composition according to any one of claims 1-3, wherein at least 50 wt% of said monofunctional reactive diluents is absent an aromatic ring.
- 20 5. The composition according to any one of claims 1-4, wherein said composition has a viscosity of less than 3,000 cps in at least part of the range 40°C-60°C.
6. The composition according to any one of claims 1-5, wherein a coating obtained by curing said composition has a glass transition temperature of less than -30 °C.
- 25 7. The composition according to any one of claims 1-6, wherein said composition comprises less than 5 wt%, relative to the total weight of the composition, of silicone oligomers.
- 30 8. The composition according to any one of claims 1-6, wherein said composition is absent any silicone oligomers.
9. The composition according to any one of claims 1-8, comprising an oligomer having ethylene oxide and butylene oxide moieties.

Cont
2nd
AI

10. The composition according to any one of claims 1-9, comprising an oligomer having diisocyanate residues, wherein at least 50 mole% of the diisocyanates used to form the oligomer is absent a cyclic structure.
- 5
11. The composition according to any one of claims 1-10, comprising an alkoxyated aliphatic diluent.
12. The composition according to any one of claims 1-11, comprising a silane
- 10 adhesion promoter.
13. The composition according to any one of claims 1-12, wherein said composition, after cure, has a secant modulus of less than 1.5 MPa.
- 15
14. A radiation-curable composition comprising:
- (i) a radiation-curable oligomer;
 - (ii) 0-45 wt% of one or more reactive diluents;
- wherein
- said oligomer comprises diisocyanate residues;
- 20 at least 50 mole % of the diisocyanates used to form said oligomer is absent a cyclic structure; and
- said composition has a viscosity of less than 10,000 cps at 25 °C.
15. The composition of claim 14, wherein at least 65 mole% of the diisocyanates
- 25 used to form said oligomer is absent a cyclic structure.
- 906
B7
16. The composition according to any one of claims 14-15, wherein said composition comprises less than 10 wt% of monofunctional reactive diluents.
- 30
17. The composition according to any one of claims 14-16, wherein said composition, after cure, has a secant modulus of less than 5 MPa.
18. The composition according to any one of claims 14-17, wherein said composition has a viscosity of less than 3,000 cps in at least part of the temperature
- 35 range 40°C-60°C.

9/20/20

[illegible]